

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**



Attorney Docket No.: 1510-1069

PATENT

IN THE U.S. PATENT AND TRADEMARK OFFICE

Applicant: AXEN et al. Conf. No.: Unknown  
Appl. No.: 10/691,499 Group: Unknown  
Filed: October 24, 2003  
For: METHOD OF MAKING STRUCTURED CERAMIC  
COATINGS AND COATED DEVICES PREPARED  
WITH THE METHOD

L E T T E R

Assistant Commissioner for Patents  
P.O. Box 1450  
Alexandria, Virginia 22313-1450

Date: January 28, 2004

Sir:

Under the provisions of 35 U.S.C. § 119 and 37 C.F.R. § 1.55(a), the applicant(s) hereby claim(s) the right of priority based on the following application(s):

<u>Country</u>	<u>Application No.</u>	<u>Filed</u>
SWEDEN	0203224-1	October 31, 2002

A certified copy of the above-noted application(s) is(are) attached hereto.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 25-0120 for any additional fee required under 37 C.F.R. §§ 1.16 or 1.17; particularly, extension of time fees.

Respectfully submitted,

YOUNG & THOMPSON

By

Benoît Castel  
Benoît Castel, #35,041  
745 South 23<sup>rd</sup> Street, Suite 200  
Arlington, Virginia 22202  
(703) 521-2297

BC/psf

Attachment

# PRV

PATENT- OCH REGISTRERINGSVERKET  
Patentavdelningen

## Intyg Certificate



*Härmed intygas att bifogade kopior överensstämmer med de handlingar som ursprungligen ingivits till Patent- och registreringsverket i nedannämnda ansökan.*

*This is to certify that the annexed is a true copy of the documents as originally filed with the Patent- and Registration Office in connection with the following patent application.*

(71) *Sökande*                      *CerBio Tech AB, Uppsala SE*  
*Applicant (s)*

(21) *Patentansökningsnummer*    *0203224-1*  
*Patent application number*

(86) *Ingivningsdatum*                      *2002-10-31*  
*Date of filing*

*Stockholm, 2003-12-08*

*För Patent- och registreringsverket*  
*For the Patent- and Registration Office*

*Hjördis Segerlund*  
*Hjördis Segerlund*

*Avgift*  
*Fee*                      *170:-*

Ink. f. Patent- och Ret. v. 1.0

2007-10-01

1

H. Ludvig Brann

## **METHOD OF MAKING STRUCTURED CERAMIC COATINGS AND COATED DEVICES PREPARED WITH THE METHOD**

### **The Field of the Invention**

- 5 The present invention relates to a method for low temperature deposition of multi-phase and multi-layered coatings of ceramic compositions with hydraulic binder phases on substrates, which may be metals, polymers as well as ceramics.

### **Background of the Invention**

- 10 Some bioceramics are of particular interest within orthopaedics and odontology, e.g. hydroxyapatite, fluoroapatite, calcium phosphates, calcium carbonate and Bioglass®. These materials can also be made more or less bio-resorbable, i.e. they may be dissolved in the body and replaced by natural tissues. This group of ceramics is explored e.g. for orthopaedic metal implants coated with a surface layer
- 15 of hydroxyapatite, and various bone graft materials based on calcium phosphates and/or calcium carbonates e.g. Norian SRS® described in: "Norian SRS versus external fixation in redisplaced distal radial fractures - A randomized study in 40 patients", by P. Kopylov, K. Runnqvist, K. Jonsson and P. Aspenberg, Acta Orthop Scand, 1999; 70 (1) 1-5.

20

Bioceramics are described in: Bioceramics by A. Ravaglioli and A. Krajewski, Chapman and Hall, 1992. Hydroxyapatite and calcium phosphate coatings on titanium are out-lined in: Titanium in Medicine by D. M. Brunette, P. Tengvall, M. Textor and P. Thomsen, Springer-Verlag 2001, ISBN 3-540-66936-1. Artificial bone

25 graft materials are described in the patent application: "Ceramic material and process for manufacturing" (SE-0104441-1), filed 27-12-2001; and "Bioresorbable ceramic composite", US 6,027,742.

30

The precipitation of apatite from solutions is described e.g. in: P. Li, P. Ducheyne, "Quasi-biological apatite film induced by titanium in a simulated body fluid", J. Biomed. Mater. Res., 41, 341-348 (1998); and H.B. Wen, J.G.C. Wolke, H.J.R. de Wijn, Q. Liu, F.Z. Cui, K. de Groot, "Fast precipitation of calcium phosphate layers



Hilti Patent AG

7102-10-8 1

Hilti AG, Kempten

those depicted in Fig. 1. With the technique according to the present invention, surface coatings with controlled variations in terms of chemical composition, phase composition, porosity, surface roughness, mechanical properties, biocompatibility, etc can be achieved.

5

The present invention provides a method for producing a multi-structured and/or multi-phased ceramic coating in one hydration step. In a basic form, said method comprises application of a non-hydrated ceramic component (or a mixture comprising at least one hydraulic component, which is preferably a phase of calcium aluminate on a substrate, and on top of this layer, a layer of another material, e.g. a biocompatible or bioactive material, and curing said aggregate using a water-based medium. By this method, a multi-structured, a multi-phased ceramic coating, or a combination of the both, can be obtained.

15

The method according to the present invention can be combined with any coating method involving application of one or more non-hydrated ceramic materials on a substrate. The method according to the present invention is also applicable if the applied ceramic layers are composed of different ceramic materials or comprise mixtures.

20

The surface coating method according to the present invention is preferably used for producing a biocompatible coating. This biocompatible coating may suitably be used for producing general implants, or specifically implants for orthopaedic and dental applications. The present invention also relates to a device, the surface of which has been coated with a biocompatible coating according to the present invention. The biocompatible coatings may also be used as carriers of therapeutically active drugs, as well as for applications within the fields of micro-structure technology and tribology.

30

#### **Brief Description of Drawings**

Fig. 1. Schematic general drawings of a) homogenous coating, b) multi-phase coating, and c) multi-layered coating, which can be achieved using the coating method according to the present invention.

Patent Application

4

2002-10-31

Hans-Joachim Kossow

Fig. 2. Scanning electron cross-section image of double layered coating consisting of a pure hydrated calcium aluminate layer in contact with the substrate and an outer layer of calcium aluminate with 10 wt.% titania.

5

### Detailed Description of the Invention

The present invention relates to a low temperature method to produce surface coatings based on chemically bonded hydraulic ceramics, in particular all phases of calcium aluminate are applicable to the invention. The present invention describes different ways of controlling the microstructure, porosity, thickness, surface roughness, phase composition and biocompatibility of a coating system.

The method according to the present invention allows the deposition of coating structures combining mechanically strong and chemically stable compounds (primarily hydrated calcium aluminate) with osseocompatible or bio-resorbable compounds, such as hydroxyapatite and calcium carbonate. Coatings may be designed e.g. with an outer layer of the bioresorbable substance, and an inner layer of a hydrated ceramic having better mechanical properties and adhesion to the substrate.

20

One object of the present invention is to provide a surface coating method comprising the steps of preparing several powder mixtures of different chemical composition containing at least a non-hydrated hydraulic ceramic powder binder phase, pre-treating a substrate surface, to increase the adhesion between the substrate and the ceramic coating, applying said powder mixtures of different chemical composition on the substrate as layers on top of each other, and hydrating the different powder layers in a curing agent. Said non-hydrated hydraulic ceramic powder essentially comprises calcium aluminate, calcium silicate or calcium sulphate or mixtures thereof.

30

To produce multi-layered structures, the deposition may take place in several consecutive steps. A preferred version involves a first deposited layer containing mainly fine-grained (less 1  $\mu\text{m}$ ) calcium aluminate particles, since this produces a

MATERIALS

1-31

1-31

dense and mechanically strong layer in contact with the substrate. This is followed by additional depositions of more coarsely grained, or agglomerated dispersions producing rougher and pore porous layers after hydration. An outer layer is then deposited containing larger amounts of bioactive additives such as Bioglass®,  
5 hydroxyapatite or fluoroapatite.

The present invention provides an improved coating method for coating various devices, such as medical devices, which improved coating method is related to the methods described in the earlier patent applications SE-0104440-3, "Coating  
10 method and coated devices" (filed December 2001); and SE-0200637-7, "Ceramic surface layers and coated devices (filed March 2002).

Due to the simple application technique for the powders and the low temperatures required for hydration, the chemical composition and the phases of compounds  
15 contained in such a composition, as well as the microstructure and porosity of the different layers, can be controlled much better than with the prior art techniques.

Throughout this application the term "biocompatibility" is used a number of times implying certain properties on the material or surface in question. However, it  
20 should be noted that biocompatibility is used as a generic term for the different properties that are required or desirable for materials that are to be in contact with biological tissues. Moreover, the materials have also to be used/prepared in the right way and for suitable applications. Another frequently used term is "osso-compatible", which implies that a material is especially advantageous for use in  
25 contact with bone tissue. The term "bioactive" means that a material being stimulates the in-growth of an implant in for example bone tissue. The term Bioglass® which is used several time in the description is a trade name for a family of phosphorous glasses of good biocompatibility.

### 30 Multi-phase and multi-layered coatings

In addition to homogenous single-phase coatings, improved performance is often achieved with multi-phase and multi-layered coatings systems. Reasons to use such coating systems may be to improve the adhesion to the substrate, to increase



the toughness, hardness or biocompatibility; to reduce internal stresses in the coatings; or to control volumetric changes during coating manufacturing. The concepts of multi-phase and multi-layered coatings are illustrated by figure 1.

- 5 The different phases or individual layers may be composed of one or several of the following compounds: calcium aluminates, calcium aluminate hydrates, other hydraulic phases, e.g. calcium sulphate and calcium silicate, fluorapatite, hydroxyapatite, other apatites, calcium phosphates, calcium carbonates, carbonates-apatites mixed phases, Bioglass®, inert phases (non-hydrating phases  
10 and calcium aluminate).

The most preferred hydraulic cement used with the method according to the present invention is various forms of calcium aluminate. But the method is applicable also on other hydraulic cements, such as silicates and sulphates.

15

Like in methods disclosed in previous patent applications SE-0104440-3, "Coating method and coated devices" (filed December 2001); and SE-0200637-7, "Ceramic surface layers and coated devices (filed March 2002), the method comprises the following steps:

20

- Pre-treatment of substrate.
- Preparation of powder particles and dispersions of these in a liquid.
- Deposition of powders particles on a substrate surface, in single or multiple layers
- Hydration of hydraulic component with water, water based solutions or evaporated  
25 water

25

However, in the method according to the present invention the step of depositing powders particles the substrate surface differs from the above-mentioned methods in that layers of different chemical composition are applied on top of each other.

30

#### Pre-treatment of the substrate

The substrate pre-treatment follows the same procedures as described in SE-0104440-3, "Coating method and coated devices" (filed December 2001).

Int. Patent application

7

2002-10-31

Patent application

The pre-treatment step is preferably performed with wet or dry sand blasting generating a surface roughness with  $R_a$ -values, in the range of 0.1 to 10.0  $\mu\text{m}$ . Also other techniques resulting in similar random surface structures may be applicable, e.g. etching processes, electrolytic processes or abrasive surface treatments. The aim of the blasting is to achieve the anchoring of the coating on the substrate. Also blasting with particles of hydraulic ceramics, preferably CA, is an alternative; this provides seed points (embedded ceramic powder or particles) for the following hydration of the applied ceramic powder. Optionally, but not necessary, the substrate surface may also be pre-treated with hydration accelerating compounds, such as LiCl or other accelerators known within the field. The purpose of the pretreatment with such an accelerator is to initiate the hydrating process in a controlled way directly on the substrate surface, whereby porosity, cracking etc. is avoided at the coating/substrate interface.

The substrate used is according to the present invention Ti or alloys thereof, stainless steel, Co-Cr alloys, another biocompatible metal, polymeric or ceramic material, or any combination thereof.

#### Preparation of powder mixtures and dispersions of these

Preparation of the powder particles involves creation of a selected composition, phase structure and grain size of the hydraulic cement, which is preferably calcium aluminate or calcium silicates. In a basic form of the present invention, the ceramic powder comprises only hydraulic grains of calcium aluminate, of which several stoichiometries exist. Powders consisting of  $C_3A$ ,  $C_{12}A_7$ , CA,  $CA_2$  and  $CA_6$ , where C stands for CaO and A for  $Al_2O_3$ , are all applicable to the present invention. Such powders are commercially available products.

Said surface coating method may optionally comprise the step of preparing a powder mixture comprising adding particles or powder of one or more biocompatible or bioactive materials composed of particles or powder of one or several phases containing phosphates, fluorides or carbonates, calcium carbonate, calcium

phosphate, apatite, fluoroapatite, carbonates-apatites, hydroxyapatite and Bioglass®.

5 In addition to the hydraulic component and the additives controlling the formation of apatites and carbonates, the powder mixture may also contain additives controlling mechanical properties, expansion, curing time, etc.

10 A non-hydraulic, i.e. non-hydrating, filler may be added as described in our co-pending Swedish patent application SE-0 104 441-1 with the title "Ceramic material and process for manufacturing". The non-hydraulic filler may comprise calcium titanate or any other ternary oxide of perovskite structure according to the formula  $ABO_3$ , where O is oxygen and A and B are metals, or any mixture of such ternary oxides. A in the perovskite structure is selected from the group comprising Mg, Ca, Sr or Ba, and that the B in the perovskite structure is selected from the  
15 group comprising Ti, Zr, or Hf. The non-hydraulic filler should be present in an amount of less than 30 vol.%, preferably less than 10 vol.% of the total volume of the ceramic ingredients. But, all material compositions disclosed in said application also apply as coating materials in the present invention.

20 Also, the expansion controlling additives described in the patent application PCT/SE99/01803, "Dimension stable binding agent systems", are relevant to the present invention, primarily calcium silicates and fumed silica (very finely grained silica).

25 The surface coating method according to the present invention may also optionally include removing residual water and/or organic material in the powder material.

30 According to the present invention the surface roughness and porosity are controlled by the choice of particle size of the powder/particle mix. Thus, the method according to the present invention optionally comprises reducing the powder grain size. Small grain sizes allow for smoother coatings and for even coverage of micro-structured surfaces. When these properties are required, the

powder grain size is preferably below 10  $\mu\text{m}$  and more preferably between 0.1 and 3  $\mu\text{m}$ . Larger grains and agglomerated grains also produce more porous coatings.

The applied non-hydrated ceramic layer/layers may also be compacted prior to the final hydration. Such compacting can be achieved by using cold isostatic pressing (CIP), hot isostatic pressing (HIP), or by passing a laser beam across the surface. After the compaction step, the degree of compaction of the powder layer is increased between 30 and 80 % and the porosity reduced to 30-45 vol%.

According to the present invention the surface roughness is also controlled by the choice of dispersion liquid for the particle mix. Dispersion liquids of relevance are water, alcohols, oils, acetone, other hydrocarbons, plasticizers, etc. Properties of the liquid to consider are viscosity, vapour pressure, dispersion effects as well as wettability to powder particles and to substrate. Water or water-based solvents lead to an immediate start of the hydration. Non-water solvents are combined with post-curing, meaning that the actual curing is performed in a separate step.

Ethanol produces smoother surfaces than acetone due to better dispersion ability. For water-based liquids, the surfaces structure is controlled by the use of water dissolvable dispersing agents and plasticisers.

For the creation of multi-layered coatings, powder mixtures of different composition and solvents may be prepared for deposition in several subsequent steps.

Optionally, a component which accelerates or retards the hardening process may be added to the curing agent or the powder material in order to enhance adhesion to a substrate.

#### Deposition of powder particles on substrate surface

The powder-solvent mixture is applied to the substrate as one or several thin layers. Various deposition techniques may be used, e.g. dipping, spraying, etc. All deposition techniques described in our co-pending Swedish patent application SE-

DE 10 2002 00000000

00000000-0000

10 DE 10 2002 00000000

0200637-7, "Ceramic surface layers and coated devices (filed March 2002) are of relevance to the present invention.

5 The application of the powder material on the substrate surface is performed by a thermal spray technique, PVD or CVD deposition techniques, or applied as a tape prepared by tape casting.

10 The thickness of the coating is controlled either by the particle size, the dispersion of the particles and the powder-to-solvent ratio. For thick coatings multiple dipping or spraying can be performed.

After deposition of the particle mix, the solvent is evaporated. The evaporation may be performed by letting the particle mixture stand at room temperature in normal atmosphere, but the evaporation process is accelerated at higher temperatures.

15 The deposited surface coating according to the present invention has a thickness in the order of 0.1-500  $\mu\text{m}$ , and preferably less than 50  $\mu\text{m}$ .

#### Post-hydration

20 The most relevant procedure of the present invention to cure the deposited particle layer or layers is by post-hydration in a separate step in a water solution, water vapour or an atmosphere of controlled humidity.

25 Also the temperature affects the curing procedure. Most relevant for the invention are temperatures between 0°C and 100°C. Preferably, the curing is performed in the range of 20°C to 70°C.

#### Coatings and coated devices

30 In one embodiment of the method according to the present invention a biocompatible coating is achieved comprising a binding layer in contact with the substrate comprising mainly calcium aluminate particles of less than 2  $\mu\text{m}$ , a bulk layer comprising mainly calcium aluminate having a grain size between 3 and 30

$\mu\text{m}$ , and an outer layer comprising a bioactive material, preferably calcium phosphate, apatite, calcium carbonate or calcium fluoride.

5 The biocompatible coatings may also be used as carriers of therapeutically active drugs.

10 The present invention also relates to a surface coated device, comprising a substrate and a surface coating covering at least a section of the substrate surface, wherein the surface coating is the biocompatible surface coating made by using the surface coating method according to the present invention and the substrate is Ti or alloys thereof, stainless steel, Co-Cr alloys, another biocompatible metal, polymeric or ceramic material, or any combination thereof. The surface coated device may be a medical device, medical device for implantation, artificial orthopedic device, spinal implant, joint implant, attachment element, bone nail, bone screw, or a bone  
15 reinforcement plate.

#### EXAMPLE

The surface of a stainless steel substrate, in the form 50 mm long and 4 mm in diameter rods, were pre-treated by sand blasting with 90 mesh aluminum oxide grit  
20 to a surface roughness of  $R_a$  between 0.6 and 0.7  $\mu\text{m}$ .

A calcium aluminate powder from Lafarge Aluminates, Ternal White® was selected. This is a calcium aluminate with a ratio of  $\text{Al}_2\text{O}_3$  and  $\text{CaO}$  of about 70/30. However, any other similar calcium aluminate powder is also possible to use for the same  
25 purpose.

The grain size of the calcium aluminate powder was reduced by ball milling. The milling reduced the size of 90% of the grains to less than 10  $\mu\text{m}$ . The milling was performed with a rotating cylindrical plastic container using 10 mm in diameter silicon nitride spheres as milling medium. The milling liquid was iso-propanol. The  
30 total milling time was 72 hrs.

After milling, the milling bodies were removed by sieving and the alcohol was evaporated. Thereafter the milled powder was burnt at 400°C for 4 hours, to remove any residual water and organic contamination.

- 5 As the bioactive component, hydroxyapatite from Merck with an average grain size of 5 µm was selected.

10 For the application of a graded coating, two different slurries were prepared. The first slurry, A, consisted of the milled calcium aluminate powder and ethanol mixed with in ration 1:1 by weight. For a second slurry, B, a powder mixture of the same calcium aluminate powder was first mixed 1:1 by weight with hydroxyapatite. This combined powder was mixed in ratio 1:1 by weight with ethanol.

15 The first layer was applied by dipping the substrate in slurry A, whereafter the ethanol was evaporated in air. The second layer was applied by spraying slurry B on top of the first dried layer. Finally, the ethanol from slurry B was evaporated in air. The dried powder layers remained as a weakly cohesive multi-layered structure, covering the entire substrate.

20 Thereafter, the samples were hydrated in an upright position in a closed container with a layer of de-ionised water at the bottom at a temperature of 37 °C, leading to a saturated water vapour environment, for 3 days.

25 The procedure creates a two-layered structure of about 100 µm in total thickness. The inner coating is about 30-60 µm in thickness and consists predominately of calcium aluminate hydrates together with small amounts of non-hydrated calcium aluminates grains. The thickness of the outer layer is between 40 and 70 µm, and contains largely unaffected hydroxyapatite grains in a matrix of predominately calcium aluminate hydrates with traces of non-hydrated calcium aluminate grains.

30

## CLAIMS

1. Method of coating a substrate surface comprising the steps of:
- 5        -preparing several powder mixtures of different chemical composition,  
      wherein at least one of said mixtures comprise a non-hydrated hydraulic  
      ceramic powder binder phase,
- 10        -pre-treating the surface of a substrate, to increase the adhesion between the  
      substrate and the ceramic coating,
- 15        -applying layers of said non-hydrated powder mixtures on top of each other  
      on the substrate, and
- hydrating the different powder layers utilizing a curing agent.
2. Method of coating a substrate surface according to claim 1, **characterised in**  
      **that** the step of preparing a powder mixture further comprises adding  
      particles or powder of one or more biocompatible materials composed of  
      particles or powder of one or several phases containing phosphates,  
20        fluorides or carbonates, calcium carbonate, calcium phosphate, apatite,  
      fluoroapatite, carbonates-apatites, hydroxyapatite and phosphorous glasses  
      of good biocompatibility.
- 25        3. Method of coating a substrate surface according to any of the preceding  
      claims, **characterised in that** it further comprises the step of adding a non-  
      hydraulic filler comprising calcium titanate or any other ternary oxide of  
      perovskite structure according to the formula  $ABO_3$ , where O is oxygen and A  
      and B are metals, or any mixture of such ternary oxides, said filler being  
      present in an amount of less than 30 vol.%, preferably less than 10 vol.% of  
30        the total volume of the ceramic ingredients.
4. Method of coating a substrate surface according to any of the preceding  
      claims, **characterised in that** the step of preparing a powder mixture



includes reducing the powder grain size, preferably such that it is below 10  $\mu\text{m}$  and more preferably between 0.1 and 3  $\mu\text{m}$ .

- 5      5. Method of coating a substrate surface according any of the preceding claims, **characterised in that** the pretreatment of the substrate is performed by blasting its surface with hard particles.
- 10      6. Method of coating a substrate surface according to any of the preceding claims, **characterised by** the step of embedding fragments or powder of a hydraulic ceramic, preferably of calcium aluminate in the substrate surface.
- 15      7. Method of coating a substrate surface according to claim 6, **characterised in that** the embedding is performed by blasting the substrate surface with fragments or powder of a hydraulic ceramic, preferably with calcium aluminate.
- 20      8. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** a pretreatment of the substrate surface to a surface roughness in the range of  $R_a$  0.1 to 10.0  $\mu\text{m}$  is performed before deposition of the powder mix.
- 25      9. Method of coating a substrate surface according to any of the preceding claims, **characterised by** the step of pre-treating the substrate surface with an accelerator-agent for accelerating the hardening process.
- 30      10. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** the powder layer is applied by a thermal spray technique, PVD or CVD deposition techniques, or applied as a tape prepared by tape casting.
11. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** the applied non-hydrated ceramic powder layer/layers are compacted prior to the final hydration.

- 5
12. Method of coating a substrate surface according to claim 11, **characterised in that** the compacting is achieved by using cold isostatic pressing (CIP), hot isostatic pressing (HIP), or by passing a laser beam across the surface.
- 10
13. Method of coating a substrate surface according to claim 12 or 14, **characterised in that** the degree of compaction of the powder layer is increased between 30 and 80 % and the porosity reduced to 30-45 vol%.
- 15
14. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** it further comprises the step of adding a dispersing agent to the powder material, e.g. selected from the group comprising water, alcohols, oils, acetone, other hydrocarbons, and plasticizers.
- 20
15. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** the step of curing comprises using a curing agent in the form of a liquid or a gas.
- 25
16. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** the curing agent is a water solution or water vapour.
- 30
17. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** the step of hardening the ceramic coating comprises addition of a component which accelerates or retards the hardening process.
18. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** the step of hardening comprises controlling the temperature to be in the range of 0°C to 100°C, preferably in the range 20°C to 70°C.

19. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** the deposited coating has a thickness in the order of 0.1-500  $\mu\text{m}$ , and preferably less than 50  $\mu\text{m}$ .

5 20. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** the non-hydrated hydraulic ceramic powder is essentially calcium aluminate, calcium silicate or calcium sulphate or mixtures thereof.

10 21. Method of coating a substrate surface according to any of the preceding claims, **characterised in that** the substrate is Ti or alloys thereof, stainless steel, Co-Cr alloys, another biocompatible metal, polymeric or ceramic material, or any combination thereof.

15 22. Biocompatible coating, **characterised in that** the coating comprises a binding layer in contact with the substrate comprising mainly calcium aluminate particles of less than 2  $\mu\text{m}$ ,

20 a bulk layer comprising mainly calcium aluminate having a grain size between 3 and 30  $\mu\text{m}$ , and

an outer layer comprising a bioactive or biocompatible material, preferably calcium phosphate, apatite, calcium carbonate or calcium fluoride.

25 23. Biocompatible coating according to claim 22, **characterised in that** the coating is capable of carrying drugs.

30 24. Surface coated device, comprising a substrate and a surface coating covering at least a section of the substrate surface, **characterised in that** the surface coating is a biocompatible surface coating made by using the method according to any of the claims 1-21.

25. Surface coated device according to claim 24, **characterised in that** the substrate is Ti or alloys thereof, stainless steel, Co-Cr alloys, another biocompatible metal, polymeric or ceramic material, or any combination thereof.

5

26. Surface coated device according to any of the claims 24 to 25, **characterised in that** it is a medical device, medical device for implantation, artificial orthopedic device, spinal implant, joint implant, attachment element, bone nail, bone screw, or a bone reinforcement plate.

10

27. Surface coated device according to any of the claims 24 to 26, **characterised in that** the surface coating is the biocompatible surface coating according to claim 22.

15

20

25

30

**Abstract**

The invention describes a low temperature method for producing multi-layered or multi-phased coatings. With the technique according to the present invention, surface coatings with controlled variations in terms of chemical composition, phase composition, porosity, surface roughness, mechanical properties, biocompatibility, etc can be achieved. The method of coating a substrate surface comprises the steps of preparing several powder mixtures of different chemical composition containing at least a non-hydrated hydraulic ceramic powder binder phase, pre-treating a substrate surface, to increase the adhesion between the substrate and the ceramic coating, applying said non-hydrated powder mixtures of different chemical composition on the substrate as layers on top of each other, and finally, hydrating the powder layers in a curing agent.




Ink. L. Patent- och reg. verkst  
2002-10-31  
Hanselmann Kessner


1/1

Figure 1

a) Homogenous coating



b) Multi-phase coating



c) Multi-layered coating




Figure 2

